



TotalEnergies

Refining & Chemicals
Polymers

Polypropylene Lumicene® MR60MC2

Technical data sheet
Polypropylene – Metallocene Random Copolymer
Produced in Europe

Description

Lumicene® MR60MC2 is a metallocene random copolymer with a Melt Flow Index of 60(*) g/10 min for injection moulding. Lumicene® MR60MC2 differs from standard random copolymers by its moulding reproducibility, outstanding organoleptic properties combined with low extractables, excellent transparency and gloss, high rigidity combined with superior impact resistance.

Producers of rigid food packaging, caps and closures, medical device and packaging, houseware and kitchenware will take full advantage of the new Lumicene® random metallocene product range.

We hereby confirm that we do not use peroxide in the manufacturing of the above-mentioned product.

Characteristics

	Method	Unit	Typical Value
Rheological properties			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	60 (*)
Mechanical properties			
Tensile Strength at Yield	ISO 527-2	MPa	31
Elongation at Yield	ISO 527-2	%	10
Tensile modulus	ISO 527-2	MPa	1300
Flexural modulus	ISO 178	MPa	1250
Izod Impact Strength (notched) at 23°C	ISO 180	kJ/m ²	5
Thermal properties			
Melting Point	ISO 3146	°C	140
Other physical properties			
Density	ISO 1183	g/cm ³	0.902
Bulk Density	ISO 1183	g/cm ³	0.525

(*) MFI 60 in metallocene catalyst system processes like MFI 40-45 in standard Ziegler Natta catalyst system.

Handling and storage

Please refer to the safety data sheet (SDS) for handling and storage information. It is advisable to convert the product within one year after delivery provided storage conditions are used as given in the SDS of our product. SDS may be obtained from the website: www.polymers.totalenergies.com.

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. These are typical values not to be construed as specification limits. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within TotalEnergies Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.