



TotalEnergies

Refining & Chemicals
Polymers

Polyethylene LDPE 1022 FH 24

Technical data sheet
Low Density Polyethylene BLOWN FILM
Produced in Europe

Description

LDPE 1022 FH 24 is a low density polyethylene produced by a high pressure process.

LDPE 1022 FH 24 is a slip and anti-block formulated grade.

LDPE 1022 FH 24 is suited to many applications in the field of consumer, industrial, food or hygiene packaging such as bags, lamination and coextrusion film.

Characteristics

Property	Method	Unit	Typical value
Density	ISO 1183	g/cm ³	0.923
Melt Flow Rate (190°C/2.16 kg)	ISO 1133	g/10 min	2.3
Melting temperature	ISO 11357	°C	109
Vicat temperature	ISO 306	°C	94

Values indicated are typical for this product. Density and MFR are properties routinely measured during "the standard quality control procedure". The other figures are generated by tests not included in the "standard quality control procedure", and are given for information only.
Data are not intended for specification purposes.

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. These are typical values not to be construed as specification limits. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within TotalEnergies Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.



TotalEnergies

Refining & Chemicals
Polymers

Blown film properties

These values have been measured on 40 µm blown film.

Property	Method	Unit	Typical value (*)
Tensile Strength at Yield MD/TD (**)	ISO 527-3	MPa	12/11.5
Tensile Strength at Break MD/TD (**)	ISO 527-3	MPa	22/20
Elongation at Break MD/TD (**)	ISO 527-3	%	350/580
Elmendorf MD/TD (**)	ISO 6383-2	N/mm	72/60
Dart test	ISO 7765-1	g	95
Haze	ISO 14782	%	8

(*) Figures stated hereabove are obtained using laboratory test specimens produced with the following extrusion conditions: 45 mm screw diameter, L/D = 30, die diameter = 120 mm, die gap = 1.4 mm, BUR = 2.5:1, temperature = 185°C.

(**) MD : Machine Direction TD : Transverse Direction

Handling and storage

Please refer to the safety data sheet (SDS) for handling and storage information. It is advisable to convert the product within one year after delivery provided storage conditions are used as given in the SDS of our product. SDS may be obtained from the website: www.polymers.totalenergies.com.

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. These are typical values not to be construed as specification limits. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within TotalEnergies Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.