



**TotalEnergies**

TotalEnergies Petrochemicals & Refining USA, Inc.  
Polymers Americas

# Polypropylene 5946WZ

Technical Data Sheet  
Polypropylene – Impact Copolymer  
Produced in the United States

## Description

**Polypropylene 5946WZ** is a nucleated impact copolymer with a Melt Flow of 75 g/10min.

5946WZ is characterized by very low warpage, improved stiffness, and high impact resistance balance, excellent antistatic properties and has been formulated to allow faster cycling through early demolding.

5946WZ complies with all applicable FDA regulations for food contact applications.

5946WZ has been developed specifically for the injection molding of thin-walled articles and compounding.

## Characteristics

	Method	Unit	Typical Value
<b>Rheological Properties</b>			
Melt Flow	D-1238	g/10 min	75
<b>Mechanical Properties</b>			
Tensile Strength at Yield	D-638	psi (MPa)	3,700 (26)
Elongation at Yield	D-638	%	6
Flexural Modulus	D-790	psi (MPa)	180,000 (1,240)
Izod Impact Notched @ 23°C	D-256	ft.-lbs/in. (J/m)	1.4 (75)
<b>Thermal Properties<sup>(1)</sup></b>			
Melting Range	TOTAL Method	°F (°C)	320-329 (160-165)
Unannealed Heat Deflection	D-648	°F (°C)	230 (110)
<b>Other Physical Properties</b>			
Density	D-1505	g/cm <sup>3</sup>	0.905

Polypropylene

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

Rev: Sept 2021

TOTALENERGIES PETROCHEMICALS & REFINING USA, INC.  
POLYMERS AMERICAS  
1201 Louisiana Street  
Suite 1800  
Houston, TX 77002  
www.polymers.totalenergies.com

TECHNICAL CENTER  
P.O. Box 1200  
Deer Park, Texas 77536  
Phone: 281-884-7500

**1-800-344-3462**

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TotalEnergies products must be guided by the users own methods for selection of proper formulation. TotalEnergies Petrochemicals & Refining USA Inc. disclaims any responsibility for misuse or misapplication of its products. TotalEnergies MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TotalEnergies' liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.