



**TotalEnergies**

Refining & Chemicals  
Polymers

## Description

MDPE HF 513 is a medium density polyethylene produced by slurry loop low pressure process with hexene as co-monomer.

MDPE HF 513 is a semi-high molecular weight polyethylene giving excellent mechanical properties. It shows a broad molecular weight distribution ensuring outstanding processability.

MDPE HF 513 can be used alone, blended or coextruded in a wide variety of blown film applications : consumer, industrial, food or hygiene packaging.

## Characteristics

Property	Method	Unit	Typical value
Density	ISO 1183	g/cm <sup>3</sup>	0.934
Melt Flow Rate at 190°C/2.16 kg	ISO 1133	g/10 min	0.15
Melt Flow Rate at 190°C/21.6 kg	ISO 1133	g/10 min	14.5
Melting temperature	ISO 11357	°C	125
Vicat temperature	ISO 306	°C	118
Flexural Modulus (0.25% max)	ISO 178	MPa	620

Values indicated are typical for this product. Density and MFR are properties routinely measured during "the standard quality control procedure". The other figures are generated by tests not included in the "standard quality control procedure", and are given for information only. Data are not intended for specification purposes.

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. These are typical values not to be construed as specification limits. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within TotalEnergies Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.



**TotalEnergies**

Refining & Chemicals  
Polymers

## Blown film properties

Property	Method	Unit	Typical value (*)
Tensile Strength at Yield MD/TD (**)	ISO 527-3	MPa	
film 20 µm			20/19
film 40 µm			18/18
Tensile Strength at Break MD/TD (**)	ISO 527-3	MPa	
film 20 µm			65/52
film 40 µm			55/52
Elongation at Break MD/TD (**)	ISO 527-3	%	
film 20 µm			400/500
film 40 µm			540/620
Elmendorf MD/TD (**)	ISO 6383-2	N/mm	
film 20 µm			11/135
film 40 µm			24/185
Dart test	ISO 7765-1	g	
film 20 µm			220
film 40 µm			290

(\*) Figures stated hereabove are obtained using laboratory test specimens produced with the following HDPE configuration: 70 mm screw diameter, L/D = 25, die diameter = 120 mm, die gap = 1.2 mm, BUR = 4.5:1, output = 100 kg/h, neck height = 100 cm, temperature = 210°C.

(\*\*) MD : Machine Direction, TD : Transverse Direction

## Handling and storage

Please refer to the safety data sheet (SDS) for handling and storage information. It is advisable to convert the product within one year after delivery provided storage conditions are used as given in the SDS of our product. SDS may be obtained from the website: [www.polymers.totalenergies.com](http://www.polymers.totalenergies.com).

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. These are typical values not to be construed as specification limits. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within TotalEnergies Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.