



**TotalEnergies**

Refining & Chemicals  
Polymers

# Polyethylene Lumicene® Supertough 40ST05

Technical data sheet  
Metallocene Polyethylene BLOWN FILM  
Produced in Europe

## Description

Lumicene® Supertough 40ST05 is a metallocene polyethylene blown film grade that is especially designed to have an excellent balance of stiffness, toughness, processability and aesthetics.

Thanks to this innovative design, Lumicene® Supertough 40ST05 brings a huge down-gauging potential in the film market especially for the collation shrink application. It can also be used in many other multilayer applications to bring the desired properties needed to down-gauge.

## Characteristics

Property	Method	Unit	Typical value (*)
Density	ISO 1183	g/cm <sup>3</sup>	0.940
Melt Flow Rate (190°C/2.16 kg)	ISO 1133	g/10 min	0.5
Melting temperature	ISO 11357	°C	127
Vicat temperature	ISO 306	°C	122

(\*) Values indicated are typical for this product. Density and MFR are routinely measured during the standard quality control procedure. The other figures are generated by tests not included in the standard quality control procedure, and are given for information only. Data are not intended for specification purposes.

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. These are typical values not to be construed as specification limits. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within TotalEnergies Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.



**TotalEnergies**

Refining & Chemicals  
Polymers

## Blown film properties

These values have been measured on a 40 µm blown film in low neck configuration.

Property	Method	Unit	Typical value (*)
Tensile Strength at Yield MD/TD (**)	ISO 527-3	MPa	19/21
Tensile Strength at Break MD/TD (**)	ISO 527-3	MPa	48/45
Elongation at Break MD/TD (**)	ISO 527-3	%	630/750
Elmendorf MD/TD (**)	ISO 6383-2	N/mm	16/155
Dart test	ISO 7765-1	g	135
Haze	ISO 14782	%	15
Gloss 45°	ASTM D2457		40

(\*) Figures stated above are obtained using laboratory test specimens produced with the following extrusion conditions: 45 mm screw diameter, L/D = 30, die diameter = 120 mm, die gap = 1.4 mm, BUR = 2.5:1, temperature = 195°C.

(\*\*) MD : Machine Direction, TD : Transverse Direction

## Handling and storage

Please refer to the safety data sheet (SDS) for handling and storage information. It is advisable to convert the product within one year after delivery provided storage conditions are used as given in the SDS of our product. SDS may be obtained from the website: [www.polymers.totalenergies.com](http://www.polymers.totalenergies.com).

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. These are typical values not to be construed as specification limits. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within TotalEnergies Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.